

ICDD and the The Powder Diffraction File

Past, Present and Future

The following text is based on an article previously published by the International Centre for Diffraction Data and written by Deane K. Smith and Ron Jenkins.

INTRODUCTION

The **Powder Diffraction File (PDF)** has been the primary reference for powder diffraction data since the Dow Chemical Company allowed its data, first published by Hanawalt, Rinn and Frevell (1938), to be reprinted in 3"x5" card format under the auspices of the American Society for Testing and Materials (ASTM). The importance of the diffraction information was recognized by the early pioneers in the field who formed a Joint Committee for Chemical Analysis by Powder Diffraction Methods co-sponsored by ASTM Committee E-4, the Crystallographic Society of America and the British Institute of Physics. This reprint appeared in 1941 as Set 1 of the **PDF**. Since this date, a total of 45 sets have been published, with over 71,000 diffraction patterns.

The primary information in the **PDF** is the collection of d-I data—the d-spacing (d) determined from the angle of diffraction and the intensity (I), experimentally measured under the best possible conditions for a phase-pure material. These data provide a “fingerprint” of the compound because the d-spacings are fixed by the geometry of the crystal and the intensities are dependent on the elements and their arrangement in the crystal structure. Thus, the d-I data may be used for identification of unknown materials by locating matching d-I data in the **PDF** with the d-Is obtained from the unknown. Identification is the most common use for the **PDF**, but the presence of considerable supporting information on each compound allows further characterization of the compound under study. Examination of the crystal data, Miller indices, intensity values and scale factors, physical property data, and the reference provide useful information to further the knowledge of the sample. A detailed description of the **PDF** may be found in Jenkins and Smith (1985 and 1987).

To meet the needs of diffractionists, the **PDF** is continually revised and updated with new and improved information. The increased use of computers for analysis of diffraction data and the increasing size of the File require greater accuracy of the reference information. Both improved instrumentation and more sophisticated analyses have placed more stringent requirements on how data are collected, reviewed and presented, particularly in computer-readable form. This paper will review the history and present status of the **PDF** and examine the current activities of the Joint Committee on Powder Diffraction Standards (JCPDS)-International Centre for Diffraction Data (ICDD) with respect to future improvements in the **PDF** and related products.

THE HISTORY OF THE PDF

The original form of publication of the **PDF** was as 3"x5" file cards formatted so that the index lines, which were the three strongest d-spacings, were placed at the top edge of the card and the full d-I list and supporting information filled the remaining space, Figure 1-1. This format was devised to use the search scheme proposed by Hanawalt and Rinn (1936). By placing the cards in a drawer in "Hanawalt" order, the user could thumb through the cards examining the index lines to find a match. As the number of cards increased with Sets 2 (1945) and 3 (1949), the stack of cards became quite large. The larger number of entries made the **PDF** more useful because of the increased coverage, but it was also cumbersome to use for identification. A book-form Search Manual was devised in 1950 by the **PDF** editor, W. P. Davey. This manual was prepared by typing one-line search entries with the three strongest lines, the chemical formula and the **PDF** number for each compound, ordering the strips in a Termitrex holder, and photographing the assembly for offset printing. With the publication of Set 3 in 1949, the **PDF** contained about 2,500 entries. Set 4 (1953) and Set 5 (1955) brought the **PDF** up to 4,500 entries and marked the end of the first era of **PDF** history.

Figure 1-1: Card image for $Ce_2(SO_4)_3$ from PDF Set 1 as issued in 1941

d	5.5	2.85	3.03	d in A $\lambda = .708$	$\frac{I}{I_1}$	d in A $\lambda = .708$	$\frac{I}{I_1}$
$\frac{I}{I_1}$	1.00	1.00	0.80	9.5	0.06	1.82	0.02
I	50	50	40	8.0	0.02	1.76	0.12
$Ce_2(SO_4)_3$				6.7	0.04	1.71	0.30
				6.1	0.50	1.68	0.12
				5.5	1.00	1.63	0.04
				4.85	0.04	1.56	0.14
				4.33	0.16	1.495	0.04
				3.90	0.50	1.463	0.04
				3.03	0.70	1.430	0.04
				2.85	1.00	1.370	0.04
				2.71	0.04	1.320	0.20
				2.60	0.02	1.275	0.08
				2.47	0.14	1.260	0.08
				2.37	0.44	1.220	0.06
				2.27	0.14	1.185	0.02
			Z =				
a =	b =	c =		2.15	0.35	1.165	0.04
A =	C =			2.08	0.04	1.135	0.02
D =				2.01	0.04	1.105	0.02
n =	$\omega =$	$\epsilon =$		1.93	0.04	1.084	0.04
				1.87	0.60	1.052	0.04

In the time period 1941-1955, the **PDF** overcame many of the problems of a fledgling database. The financial support was initially based on contributions from industry and scientific societies, but by 1955 the **PDF** was becoming self-supporting through sales revenue. The offices of the Joint Committee moved from the Pennsylvania State University to a location in downtown State College, Pennsylvania, U.S.A. for three years, and then to ASTM headquarters in Philadelphia, Pennsylvania, U.S.A. An associateship was established at the U.S.A. National Bureau of Standards to collect data under controlled and reproducible conditions. This associateship provided d-I data on common, important compounds to replace multiple entries in the earlier sets and greatly improved the accuracy of the **PDF**. These data were collected on diffractometers rather than cameras. Some of the individuals who made significant contributions at this early stage were: W.P. Davey, A.S. Beward, W.L. Fink, H.W. Pickett, A.J.C. Wilson and L.L. Wyman. The next ten years saw

regular issues of new sets of d-I data with 1,000 to 1,500 new entries each year. Several new search aids were developed including Keysort and IBM cards, the Fink Index, the Matthews Index, and the Fink Graphical Index. Of these hard copy products, only the Fink Index has survived the test of time, and it has not been prepared since 1982 except for some subfiles of the **PDF**. In 1962, the d-Is, formulas, and **PDF** numbers were first keyboarded for a computer-readable database. The presence of these data in computer-readable form allowed the 1965 Search Manual to be computer composed. The availability of the data on magnetic media spurred the development of computer-based search/match schemes and the beginning of the next era. Three important individuals during this era were the editors of the **PDF**, G.W. Brindley and J.V. Smith, and Computer Consultant, G.G. Johnson, Jr.

During the first two stages, the Joint Committee evolved from a small group of volunteers who initiated the **PDF** to a small paid staff operating at ASTM and acting as editors under the guidance of a committee of volunteer scientists who reviewed the progress of this staff and recommended policies and products. By 1965, there were three committees: Finance, Technical and Editorial. The membership of the Joint Committee was about 30, and the meetings were simple, with each subcommittee meeting on a separate day during a week each summer. Most members were active on all committees. A Board of Directors consisting of 4 members directed the operations: W.L. Fink, Chairman; R.G. Simard, General Manager; A.W. Danko, Chairman, Technical Committee; and L.L. Wyman, Treasurer.

The year 1969 was a major turning point in the history of the **PDF**. For a variety of reasons, the operations were moved from ASTM headquarters to another location in Philadelphia, and the Joint Committee was incorporated as a separate corporation in the state of Pennsylvania. The name was changed to the Joint Committee on Powder Diffraction Standards (JCPDS). In 1971, the JCPDS moved to its headquarters in Swarthmore, PA where it remained for twenty years. The size of the staff increased as production increased, and the number of volunteers also increased. The number of meetings increased to two each year, and the additional subcommittees required more time and concurrent sessions. Currently, there are many specific subcommittees of the Technical Committee alone. Grants-in-aid were established to sponsor the collection of new data at universities, and these projects have become major sources of new data.

The period 1965–1978 saw several new products. The JCPDS sponsored an on-line search service, 2dTS, as the first computer-based search/match activity using the computer-readable database. Several individuals also developed programs for identifying crystalline phases using the d-I computerized information. Part of this development was spurred by the prospect of soft-landing a diffractometer on the moon. Automated powder diffractometers (APDs) were developed by many manufacturers using the **PDF** for phase identification as part of the supplied software. The d-I database provided the basis for the search/match procedures, but the final evaluation of the results required consulting hard copy forms of the **PDF** for the supporting information. Computer storage limitations were the main reason why the information in the database was usually distributed and utilized on magnetic tape. In spite of increased information density on the magnetic tape, the **PDF** soon exceeded the capacity of a single tape. Other new products included several hard copy subfiles, such as Minerals and Metals and Alloys, to make the **PDF** more amenable to identification in these specialty areas.

In 1978, the corporation name was changed to JCPDS-International Centre for Diffraction Data (ICDD) to reflect the international use of the **PDF** and the increased diversity of products with the marketing of Crystal Data. The role of the computer

in future products was recognized, and a project was begun to keyboard and re-evaluate all the data which comprise the **PDF**, including the supporting documentation. This re-evaluation checked for internal consistency of unit cells, d-spacings, and symmetry wherever possible. This project was completed in 1984, and the resulting database allows a computer display of the data-card image, so no hard copy form is needed. The increased packing density of information on computer media has permitted the distribution of this database in several forms including the CD-ROM. The increased use of the computer-based **PDF** and the problems of storage of the classic cards prompted the JCPDS-ICDD to discontinue the production of cards in 1987, leaving books as the only hard copy form published.

Table 1-1: Distribution of Patterns in PDF Sets 1-46

The subfiles have also been updated with the following numbers of non-deleted patterns in each subfile:			
Cements	315	Minerals	4,278
Common Phases	3,200	NBS (NIST)	1,937
Corrosive	14,164	Pharmaceutical	122
Education Package	1,034	Pigment and Dyes	196
Explosives	158	Polymers	319
Forensic	3,012	Superconductors	265
Metals and Alloys	12,150	Zeolites	787
The following statistics are from Sets 1-46 (63,557 patterns):			
Inorganic	46,035	Dual	1,225
Organic	18,201	Deleted	11,663
Distribution of Quality Marks:			
Stars	7,557	Unknown Quality	23,058
Indexed	16,468	Calculated	3,659
Poor Quality	12,716	Rietveld	99

As of October 1996, the **PDF** contained 46 data sets with 75,011 diffraction patterns, deleted patterns included. These patterns are divided into the categories presented in Table 1-1. Many patterns are classified in more than one subfile. Each individual entry contains, as a minimum, a list of the d-I pairs, the chemical formula, the mineral name if appropriate, a unique identification (**PDF**) number, and a reference to the original source of the data. In addition to this information, supplemental data may include: the crystal unit cell and symmetry, Miller indices, physical constants, experimental details, and other comments such as preparation techniques and the chemical analysis. Figure 1-2 shows a modern card image which is to be compared with Figure 1-1 to illustrate the changes that time and changing needs have implemented. In addition to a change in the format, most early data have been replaced with more accurate and expanded data and more documentation, including the crystal parameters where they were not known before.

In accordance with the nonprofit classification of the corporation, the research and development activities include sponsoring programs for the improvement of the quality of diffraction data. In addition to the associateship established at the National Bureau of Standards (now the National Institute of Standards and Technology), grants-in-aid were awarded to many universities for collecting new and improved data on compounds under study in their research projects and for the development of computer programs for analyzing diffraction data.

Figure 1-2: Card image for $Ce_2(SO_4)_3$ from PDF Set 1 as printed in 1995 format.

1- 208									
$Ce_2(SO_4)_3$				dÅ	Int	hkℓ	dÅ	Int	hkℓ
Cerium Sulfate				9.5	6		1.56	14	
				8.0	2		1.50	4	
				6.7	4		1.46	4	
				6.1	50		1.43	4	
				5.5	100		1.37	4	
Rad. MoKα ₁	λ 0.709	Filter Beta	d-sp	4.85	4		1.32	20	
Cut off	Int.		I/I _{0c}	4.33	16		1.28	8	
Ref. Hanawalt, J., Rinn, H., Frevel, L., <i>Anal. Chem.</i> , 10 457 (1938)				3.50	50		1.26	8	
				3.03	80		1.22	6	
Sys.	S.G.			2.85	100		1.19	2	
a	b	c	A C	2.71	4		1.17	4	
α	β	γ	Z mp	2.60	2		1.14	2	
Ref.				2.47	14		1.11	2	
D _x	D _m 3.912	SS/FOM		2.37	14		1.09	4	
Color Colorless, green				2.27	14		1.05	4	
CAS#: 13454-94-9, Color and measured density from Data on Chemicals for Ceramic Use, <i>National Research Council Bulletin 107</i> . Decomposition temperature is 920 C at 746 mm.				2.15	35				
				2.08	4				
				2.01	8				
				1.93	6				
				1.87	60				
				1.82	2				
				1.76	12				
				1.71	20				
				1.68	12				
				1.63	4				

STRUCTURE AND OPERATION OF THE JCPDS—ICDD

As indicated above, the JCPDS-ICDD consists of two parts: a permanent staff and voluntary scientific and technical advisers. This structure is somewhat parallel to ASTM, one of the parent organizations. The headquarters is now located in Newtown Square, Pennsylvania (after a time of twenty years in Swarthmore, Pennsylvania) where the 31 employees are responsible for producing and marketing the **PDF**. A bibliographer and several field-specific editors work under contract to locate and review the diffraction data which comprise the **PDF**. The volunteer members meet twice a year to discuss progress, to recommend new products and to consider ways to be of service to the diffraction community. The corporate business is conducted at the Annual Meeting in March of each year.

The office staff is composed of three major areas responsible for the **PDF**—Business, Database, and Technical. Although the printing of hard copy products is done outside, the typesetting, the mastering of the CD-ROM, as well as most other operations, are done in-house. As the computer became more important in the development of the **PDF**, more of the operations have been undertaken by the office staff. The General Manager is responsible for overseeing this operation and reports to the Board of Directors. The current General Manager is R. Jenkins. Previous General Managers include A.S. Beward, R.G. Simard, A.W. Danko, J.W. Caum, J. Mesick and D. Richardson.

The volunteers comprise over one hundred members of the JCPDS—ICDD. They are employed by industry, government and academia in about equal proportions. Also, 20 percent of these members are from outside the U.S. The membership is structured into several special and two major operational committees and many subcommittees as listed in Table 1-2. The Technical Committee is responsible for recommending products, procedures and projects to the Board of Directors. The Finance Committee oversees the fiscal operations, proposes the annual budget, and recommends the disbursement of funds for projects. The Board of Directors, which is elected by the membership, is responsible for: setting the policies of the JCPDS—ICDD; final approval of all projects; approving the budget; and monitoring the use of the funds. In addition to direct products involving the **PDF**, the JCPDS—ICDD

sponsors a grants-in-aid program to assist researchers in the acquisition of new diffraction data and in educational courses for training new diffractionists. The current Chairman is R. Snyder. Previous Chairmen include W.P. Davey, H.W. Rinn, W.L. Fink, L.L. Wyman, J.D. Hanawalt, G.J. McCarthy, D.K. Smith, L.K. Frevel, and G.G. Johnson, Jr.

Table 1-2: Committees and Subcommittees of the JCPDS-ICDD

<u>Board of Directors</u>
Bylaws Committee
Crystal Data Management Board
Denver Conference Integration Committee
Electron Powder Diffraction Committee
Employee Benefits Committee
Grants-in-Aid Committee
Journal Oversight Committee
Long-Range Planning Committee
Membership Committee
Member Travel Support Committee
Scholarship Committee
Finance Committee
Budget Review Subcommittee
Sales and Marketing Subcommittee
Technical Committee
Ceramics Subcommittee
Crystallographic Database Subcommittee
Crystallographically Derived Patterns Subcommittee
Data Collection/Analysis and Diffraction Problems Subcommittee
Education Subcommittee
Electron Diffraction Subcommittee
Metals and Alloys Subcommittee
Minerals Subcommittee
Neutron Powder Diffraction Subcommittee
Organic and Forensic Subcommittee
PDF Database Subcommittee
PDF Editorial Staff Subcommittee
Search/Match Methods Subcommittee
Target Systems for Technical Committee Activity Subcommittee

COLLECTION AND EVALUATION OF PDF DATA

Since 1965, 2,000 new patterns have been added yearly to the **PDF**. Each year approximately 1,200 of these patterns are retrieved from the open literature, 300 are provided by regular supporters of the **PDF**, and 500 are provided by the grants-in-aid program sponsored by the JCPDS—ICDD. To collect the literature data, the JCPDS—ICDD employs a data acquisition staff to search the scientific literature. Approximately 180 scientific journals are manually scanned and the remaining literature is searched through an on-line information retrieval service. These literature searches, along with data which are obtained by encouraging authors to supply patterns which were implied in a paper but not published, yield 2,000 to 2,500 patterns annually. The desired data are then extracted by the editorial staff and then keyboarded for evaluation. The quality of these patterns is highly variable.

The patterns from the grants-in-aid projects are also keyboarded if they are not automatically supplied in computer-readable form. The compounds studied in these projects are coordinated with the needs of the **PDF** and the expertise of the grantee. All grant data are collected by experienced diffractionists under conditions which lead to accurate results, and the samples are well-characterized, including the crystal unit-cell and symmetry. These patterns are among the best that appear in the **PDF**, and their inclusion is one reason why the quality of the **PDF** improves with time. The compounds studied are usually part of a research project and represent materials of considerable current interest. Each year, the JCPDS—ICDD awards several hundred thousand dollars in the grants-in-aid program with the amount varying depending on available funds and suitable scientific requests.

After the data are obtained from the source, prior to their inclusion in the **PDF**, they are reviewed for appropriateness and quality. Historically, the evaluation was the responsibility of several editors who had considerable experience in powder diffraction and in the characterization of the materials involved. Early d-I data were replaced by newer data as the quality improved. The evaluation of quality, however, was subjective until 1965 when the d-values and intensities were first entered into computer-readable files. This step allowed the d-I data to be checked for consistency, and this checking has become more rigorous with time. The editors initially confirmed the indexing compatibility with the unit cell reported by the author, or attempted to determine an indexing solution which would explain all the observed d-spacings.

In early 1980, a sophisticated computer program for data entry and review was developed at the National Bureau of Standards (now the National Institute of Standards and Technology) under the name NBS*AIDS83, Mighell et al., (1983). This program was designed to evaluate data for both the **Powder Diffraction File** and for **Crystal Data**. A standardized procedure is followed which checks many aspects of the data as allowed by the information available. The d-spacings are evaluated by figures of merit (deWolff, 1972 and Smith and Snyder, 1979) where unit cells are provided by the authors. These figures of merit are based on the average error in the observed diffraction angle compared to the calculated value from the refined unit cell and are used to assign the quality indicator for the data set. Crystallographic conditions are compared with the symmetry assignment provided by the author. The program also checks the consistency of the chemical formula by determining the formula weights and the density for comparison with measured values. The summary of this review is provided to the **PDF** editors to assist in their evaluation of the data. An example of NBS*AIDS83 information as stored is shown in Figure 1-3.

Figure 1-3: Display of the $Ce_2(SO_4)_3$ data in NBS*AIDS83 database format.

```

                                M           X P      P010208X1
                                3.912           0.00    P010208X3
                                568.41       0.00    P010208X4
I      CP  EDU                    13454-94-9      P010208X5
Cerium Sulfate                                P  P010208X6
Ce2 ( S O4 )3                                P010208X7
Ce2 O12 S3                                    P010208X8
ANCHAM 10 457 1938 Hanawalt, J., Rinn, H., Frevel, L.      P010208X9
Colorless, green                                CL 1P010208XB
Color and measured density from Data on Chemicals for Ceramic C2P010208XB
Use, \ITNational Research Council, Bulletin 107\RG.        3P010208XB
Decomposition temperature is 920 C at 746 mm.              4P010208XB
MoK $\alpha$ 1 0.709      F      DD      X 16.0      P010208XF
X      BB      P010208XG
9.50000 6      8.00000 2      6.70000 4      01P010208XI
6.10000 50     5.50000100     4.85000 4      02P010208XI
4.33000 16     3.50000 50     3.03000 80     03P010208XI
2.85000100    2.71000 4      2.60000 2      04P010208XI
2.47000 14     2.37000 14     2.27000 14     05P010208XI
2.15000 35     2.08000 4      2.01000 8      06P010208XI
1.93000 6      1.87000 60     1.82000 2      07P010208XI
1.76000 12     1.71000 20     1.68000 12     08P010208XI
1.63000 4      1.56000 14     1.50000 4      09P010208XI
1.46000 4      1.43000 4      1.37000 4      10P010208XI
1.32000 20     1.28000 8      1.26000 8      11P010208XI
1.22000 6      1.19000 2      1.17000 4      12P010208XI
1.14000 2      1.11000 2      1.09000 4      13P010208XI
1.05000 4      14P010208XI
B 5.50/X 2.85/X 3.03/8 1.87/6 6.10/5 3.50/5 2.15/4 1.71/2 1.32/2 4.33/2P010208X+
B 9.50/1 8.00/1 6.70/1 6.10/5 5.50/X 4.85/1 4.33/2 3.50/5 3.03/8 2.85/XP010208X*
                                EGS 91/11/25 0 0 10 91/01/16      P010208XK

```

The development of NBS*AIDS83 was the major step in initiating the comprehensive review of the older d-I data from Sets 1–32. All the data were re-evaluated, and the corrected data were entered into a master computer-readable database. The review also resulted in extensive changes to many individual, older d-I data where inconsistencies were detected. Because the NBS*AIDS83 program established a consistent set of rules for pattern evaluation, one result was the adjustment of many of the quality codes, generally downgrading many “*” patterns to “i” grade.

Currently all new data are entered into this master database following review and acceptance by the editors, maintaining it as the most current form of the **PDF**. Consequently, older hard copy forms of the **PDF** are out-of-date. This new database is now the source for all modern **PDF** products. All products, including the hard copy forms, are prepared directly from this master by appropriate computer formatting of the data. The computer-readable files allow the production of search manuals directly from the master file, minimizing the errors occurring with multiple data entry. Errors previously introduced by retyping are essentially eliminated. The book products are still based on the original 3"x5" format used in the card format, but the image has been modified to allow more efficient use of the space. Changes, such as the elimination of the three d-spacings across the top of the card image, reflect the outdated use of these entries for a search system which was superseded by the first search manuals printed.

The editing of the data is the responsibility of the Editor-in-Chief, W. F. McClune and previously three topical editors, B. Post, S. Weissmann and H.F. McMurdie, each of whom have been involved with the **PDF** for over 20 years. Other editors included, W.P. Davey, G.W. Brindley, J.V. Smith, A.S. Beward, L.G. Berry and M.E. Mrose. Prior to the implementation of the NBS*AIDS83 review, a copy of the original article containing the powder data was sent to the appropriate topical editor. This editor decided whether to continue with the review process and prepared a standard form with the extracted data. The office staff would then type the data on a master card and return a copy of the master to the editor for final review. The editor subjectively assigned one of the six quality marks, “*”, “1”, “ ”, “O”, “R”, and “C” to the data set on the basis of experience. As the approved patterns accumulated in the office, they were organized into units of 2,000 for the yearly releases of the **PDF**.

With the introduction of the NBS*AIDS83 review, the editorial process underwent considerable revision. The potentially acceptable d-I data are now keyboarded into computer-readable form and both the data and the NBS*AIDS83 output are supplied to the topical editor. The NBS*AIDS83 program provides the editor with sufficient information to make a final decision on the appropriateness of the new data to the **PDF** and to assign objectively the quality mark, which cannot be higher than the mark assigned by NBS*AIDS83. The present criteria for quality evaluation are given in Table 1-3. Once the topical editor has approved the pattern, the Editor-in-Chief checks for similar data in the **PDF** and assigns the data a position in the forthcoming **PDF** set. The acceptable data are then committed into the master database.

Table 1-3:

Several of the Tasks Performed by NBS*AIDS83

1. Formula checking including generation of an empirical formula.
2. Form of the chemical name and comparison with the formula for consistency.
3. Comparison of measured, calculated and estimated densities.
4. Validation of space group, aspect or lattice type with allowed symbols and assigned crystal system.
5. Generation of Pearson symbols for structure types.
6. Refinement of d-spacings and confirmation of indexing with extinction rules for space group.
7. Calculation of the Smith-Snyder and the deWolff figures of merit.
8. Assignment of the PDF quality mark using the initial assignment by the topical editor and the fit of the d-spacings to the refined unit cell.
9. Validation of all the editorial flags.
10. Errors and warnings are given when problems are detected.

Some patterns receive additional review by task groups of the JCPDS—ICDD. This review may occur when a subfile product is being prepared for publication. The metals and alloys subfile and the minerals subfile are reviewed periodically in order to maintain an updated version ready for reissue. This review consists of confirming the nomenclature for conformity with accepted usage and checking the presentation of the auxiliary information for completeness. For minerals, the nomenclature is governed by the Commission on New Minerals and Mineral Names of the International Mineralogical Association. Metals and alloys usually conform to the Pearson nomenclature system (Villars and Calvert, 1987).

The importance of the NBS*AIDS83 review cannot be overemphasized. In addition to checking the items in Table 1-3, the program generates considerable derived information which is stored in the master database for future reference and products. The Crystal Data cell and determinative ratios, the reduced cell and its transformation matrix, derived crystal parameters, lists of the ten lines with the strongest intensities and the ten lines with the largest d-spacings, and the formula weight are added along with all the textual information on source, preparation, etc., keyboarded from the original manuscript. Figure 1-3 shows an example of this information as recorded in the database. The original 2θ data are preserved where provided by the author. All grants-in-aid data provide the experimental 2θ values. Because of round-off problems, the 2θ s obtained by back-calculating from reported d-values are not satisfactory for error analysis and the determination of the proper figures of merit.

The data which now appear in a **PDF** image are listed in Table 1-4. The primary data and all the other information available in the manuscript are included. Information from sources other than the principal references are added where appropriate. The goal of the **PDF** is to provide the user with as much information as possible to assist in the identification of the compound.

Table 1-4:

Documentation of PDF Data	
Primary	Experimental conditions Sample description Composition Source Derived d-Is Reference for data
Secondary	Crystallographic data System Unit cell Space group Density (calculated) Internal standard References for crystal information
Tertiary	Miller indices Density (measured) Figures of merit Axial ratios Crystal Data cell Indices of refraction Reference-intensity-ratio References for physical property data
Quaternary	Synthesis or mineral locality Stability Structure type Chemical analysis

CURRENT PRODUCTS OF THE JCPDS—ICDD

The **PDF** is the principal product of the JCPDS—ICDD, but there are many supportive products. Table 1-5 is a comprehensive list of these products. Hard copy products are being replaced with computer-readable files to meet the needs of modern instrumentation. In 1986, the JCPDS—ICDD published the last set in card form. All future hard copy versions of the **PDF** will be in book form and as microfiche films. Computer-readable versions are available on a variety of media.

Search manuals, primarily the Alphabetical and Hanawalt manuals, will continue to be published in the foreseeable future. The Elemental and Interplanar Spacing Index (EISI), the latest search manual to be developed, is designed to assist the electron diffractionist by the use of chemistry and d-spacings but without the use of intensity values. It is a single-entry index which groups the compounds by largest d-spacing and chemistry and lists the ten lines with the largest d-spacings. The Fink manual, also designed primarily for electron diffraction, was last produced in 1982. Because it is a multiple-entry index, its size is too large to bind as one volume. Future editions will probably be coupled with computer-readable products or with subfiles where size is not a factor.

Table 1-5: Products of the JCPDS—ICDD

<i>The Powder Diffraction File—Inorganic and Organic</i>		
Card form (discontinued in 1987)	Metals and Alloys File	
Microfiche form	Common Phases File	
Book form	Forensic File	
Individual set	Computer-readable	
Historical data (re-edited)	Magnetic tapes	DATs
NBS Associateship Pattern File	PDF-1	PDF-2
Mineral File	Disks	CD-ROM
<i>Search Manuals</i>		
Book form	Software (provided without charge)	
Chemical Alphabetical	Johnson/Vand	
Hanawalt Method	Goehner/Garbauskas	
Fink Method	Toby POWDER SUITE	
Elemental and Interplanar Spacing Index		
<i>Educational Materials</i>		
Educational Resource Package		
Methods and Practices Manual		
Introduction to X-ray Spectrometry (ACS Audio Short Course)		
X-ray Safety Training Materials—Alcoa (non-ICDD product)		
<i>Crystal Data</i>		
Book form	CD-ROM	
Identification File on magnetic tape	Software (provided without charge)	
Minerals	Mighell/Karen	
	Harlow/Johnson	
<i>Electron Diffraction Database</i>		
Magnetic tape	Software (provided without charge)	
CD-ROM	Carr/Johnson	
<i>Journal</i>		
Powder Diffraction		

The computer-readable versions of the **PDF** are the most widely distributed form of the **PDF** today. At present there are two versions, the PDF-1 database with only PDF numbers, d-Is and compound name, and the PDF-2 database with all the data present. The main media for distribution is the CD-ROM. The magnetic media are useful where the computer is programmed to search for matches in real time. Either the medium is searched directly or the **PDF** is restructured for faster implementation, and the magnetic media are amenable to this operation.

The CD-ROM is ideal for information storage and display on personal computers. The information packing density on a compact disk is so high that the full **PDF** requires only about 50 percent of the available space of a CD-ROM. The **PDF** already fills a magnetic tape at the highest density currently available. Maximum access time on the compact disk is about 1 second for a block of data and less than 0.1 second for a contiguous search. Thus, the CD-ROM is less suitable for real-time search/match operations. When the proper index files are prepared, it is an ideal medium for look-up and display of desired information. The JCPDS-ICDD has developed programs which accompany the CD-ROM product to access information in ways similar to what would be done if the information were in book form. The 1989 version of its PC program allowed searching on **PDF** number, chemistry, mineral names, and specific d-spacing combinations. Plans for the future include the use of a Windows environment with additional searches such as Hanawalt and Fink searches and matching of specific key.

True real time search/match programs are not being developed by the JCPDS-ICDD because many are available from APD manufacturers or software developers. The JCPDS—ICDD considers itself a database producer, not a software house, but it does distribute programs developed by others. As soon as the **PDF** became available in computer-readable form in about 1963, several groups developed search programs. Some of these older programs are still being improved, and many new ones are being developed by equipment manufacturers and individual entrepreneurs. The JCPDS—ICDD will distribute any program in the public domain which will be supported by the authors. Presently, only three **PDF** programs fall into this category along with two for Crystal Data and one for the Electron Diffraction Database. The JCPDS—ICDD maintains a public bulletin board and other Internet access, but does not, at the present allow searching of its files by users.

The JCPDS—ICDD also has developed materials for educating both new and experienced diffractionists. The Education Subcommittee has been one of the most active subcommittees. A regular schedule of workshop-type courses is presented in the USA, and additional courses are offered in conjunction with scientific meetings domestic and overseas. These programs have led to the development of workbooks, which are also available for purchase at cost, to encourage the incorporation of powder diffraction methodology courses at colleges and universities. Working with the American Chemical Society, a short course was developed for audio instruction while following an illustrated manual. In addition to direct course-oriented material, the JCPDS—ICDD has assembled a Methods and Practices Manual which contains articles covering a wide variety of subjects from sample preparation to the evaluation of diffraction data. This manual is continually updated as new material becomes available. Most of the articles are reprinted from *Powder Diffraction*. Others are prepared to fill in specific subjects in the manual. This manual is available at a nominal cost.

In addition to the **PDF**, the JCPDS-ICDD has been the publisher of Crystal Data since 1963. This database of crystallographic unit-cell information is a useful supplement to the **PDF** in that it contains many more compounds than the **PDF**. In

1995, the Crystal Data File had over 210,000 entries. This File is available both on magnetic tape and on CD-ROM. Cell matching search programs have been developed by Karen and Mighell (1987) and Boolean programs by Harlow and Johnson (personal communication, 1989), and are distributed by the JCPDS-ICDD. The NBS*AIDS83 program was developed to evaluate the data for the Crystal Data File as well as for the **PDF**. The group responsible for maintaining the Crystal Data File is under the auspices of the Office of Standard Reference Data at the National Institute of Standards and Technology.

Although most new releases of Crystal Data will be in computer-readable form, there is a project in progress to bring all the mineral data up to date and print this information in a form similar to the books printed up to 1970. Because of the limited size of the mineral information, about 12,000 entries, this product is feasible. The program is being implemented by M.E. Mrose of the National Institute of Standards and Technology.

One other important product of the JCPDS—ICDD is the quarterly publication *Powder Diffraction*. This journal is devoted to disseminating throughout the world information of interest to the diffractionist. Articles range from theoretical to applied, and many new powder diffraction patterns are included. Appropriate articles are reprinted in the Methods and Practices Manual. In addition to the regular articles and data articles, the International Report section includes meeting reports, a computer section, and news of activities from the JCPDS—ICDD. The current editors are D.K. Smith, T.C. Huang, G.J. McCarthy, B.C. O'Connor, H. Toraya, and J.W. Visser, with M. Rossi as the Managing Editor.

THE COMPUTER-READABLE PDF

The first computer-readable version of the **PDF** appeared in 1962 when the **PDF** numbers, d-Is, and compound formulae were distributed on magnetic tape. That product is now known as PDF-1 (see Table 1-6). Computers of that time period were memory limited and, consequently, only essential data were included in this file. Magnetic tapes were the best way to present large blocks of data to computers. The availability of these data did encourage the development of search schemes for the identification of compounds. That stage marked the beginning of the computer age for the JCPDS—ICDD. Since that time, computer-based products have begun to take an increasingly important position in diffraction analysis.

Table 1-6:

Contents of the PDF-1	
PDF #	ds
Compound Name	Is
Compound Formula	Data Quality Mark
Subfile Code	

It was not until about 1985 that the next major step was taken. PDF-2 was introduced as soon as all the historical data from the older sets of the **PDF** were keyboarded and checked. The contents of PDF-2 are listed in Table 1-7. Essentially all the information that appeared on a card image was now available in computer-readable form. Search programs still used only the information from PDF-1; PDF-2 was used to display the supporting information on the computer screen. The first version of PDF-2 was distributed on magnetic tape, but with the availability of the

CD-ROM in the mid 1980s, it too was used as a medium for the **PDF**. Currently, the CD-ROM is one of the most popular media. Figure 1-4 illustrates the card image as presented on a PC monitor.

Table 1-7:

Contents of the PDF-2	
PDF #	Sources of Materials
Compound Name	Figures of Merit
Compound Formula	I/I(cor)
Data Collection Documentation	Data Quality Mark
Cell and Symmetry	Subfile Code
Z and Density	ds
Physical Properties	Is
Preparation and Purity	hk/s
Editor Comments	

Figure 1-4: Card image from PCPDFWIN as presented on a PC monitor

PDF # 010208, Wavelength = 1.54184																	
01-0208	Quality:	Ce ₂ (SO ₄) ₃															
CAS Number: 13454-94-9		Cerium Sulfate															
Molecular Weight: 568.41		Ref: Hanawalt, J., Rinn, H., Frevel, L., Anal. Chem., 10, 457 (1938)															
Volume[CD]: 0.00																	
Dx: Dm: 3.912																	
S.G.:																	
Cell Parameters:																	
a	b	c															
α	β	γ															
SS/FOM: F = <1 (.)			dÅ	int	h	k	l	dÅ	int	h	k	l	dÅ	int	h	k	l
I/Icor:			9.5000	6			2.7100	4					1.8200	2			
Rad: MoKα1			8.0000	2			2.6000	2					1.7600	12			
Lambda: 0.709			6.7000	4			2.4700	14					1.7100	20			
Filter:			6.1000	50			2.3700	14					1.6800	12			
d-sp: other			5.5000	100			2.2700	14					1.6300	4			
			4.8500	4			2.1500	35					1.5600	14			
			4.3300	16			2.0800	4					1.5000	4			
			3.5000	50			2.0100	8					1.4600	4			
			3.0300	80			1.9300	6					1.4300	4			
			2.8500	100			1.8700	60					1.3700	4			

FUTURE PRODUCTS

With the availability of computer-controlled diffractometers, it is now easy to collect and process digitized diffraction patterns. New experiments are now possible which analyze the peak shapes as well as position and intensity information. Such studies include structure analysis using profile fitting or whole-pattern fitting, crystallite size and strain, and quantitative analysis. It is evident that the future will need the digitized trace in addition to the current d-I data for complete diffraction

studies. PDF-3 (a digitized full pattern database) is envisioned to meet these needs. A test product for clay minerals will be the first PDF-3 undertaking. The proposed contents of PDF-3 are described in Tables 1-8 and 1-9.

Table 1-8:

Contents of the PDF-3	
PDF #	Sources of Materials
Compound Name	Figures of Merit
Compound Formula	I/I(cor)
Data Collection Documentation	Data Quality Mark
Digitized Trace Parameters	Subfile Code
Reference Sample Trace	Digitized trace
Cell and Symmetry	ds
Z and Density	Is
Physical Properties	hk ℓ s
Preparation and Purity	

Table 1-9:

Digitized Trace Parameters
Start Angle
Finish Angle
Step Size
I, 2 θ
Reference Intensity Ratio
Instrument Parameters
Standard Reference Trace

The many problems in the development of a new database such as PDF-3 are compounded because it is computer-based. The major problem is to define now what will be needed 10 or 20 years in the future. The central information in this database will be the digitized diffraction trace, but present-day instruments will evolve into the more sophisticated instruments of tomorrow and perhaps change the nature of the data that are needed. Current instruments introduce aberrations which may be minimized, and X-ray sources may become more nearly monochromatic in the future. Obviously, the most desired trace to preserve would be one with the source and instrument contributions deconvoluted to leave the sample component only. The state of the art is not quite ready for this step yet, so the alternative is to record both the instrument trace of the sample and the instrument trace of some standard taken under the same experimental conditions. The JCPDS—ICDD has instituted a project with their grants-in-aid recipients to preserve the digitized traces of the patterns they submit. The present standard is NBS SRM1976, corundum, but a study of new possibilities has led to the recommendation of LaB₆ as a good supplement to Si. A supply of LaB₆ has recently been certified by the Office of Standard Reference Data of the National Institute of Science and Technology for profile applications. Now that this standard is available to diffractionists, the project of collecting digitized traces can begin in earnest.

Other problems remain in defining the angular range of the data to be collected and the step size to be used. As with the d-I data, many of the decisions will have to be made by the diffractonist based on the nature of the sample. The range of a pattern may vary considerably. Some compounds do not produce useful diffraction information beyond $90^\circ 2\theta$ or even $60^\circ 2\theta$ in some cases. Other compounds would allow useful information to be collected beyond the range of the diffractometer. Step size is more nebulous. For a reference pattern, the step size should be as small as the most demanding application requires. Step sizes between 0.01° and $0.05^\circ 2\theta$ seem to be in common use. Most users prefer not to interpolate between data points, so the $0.01^\circ 2\theta$ step for the reference patterns seems to be the acceptable choice.

Once the database of digitized traces becomes available, it will be necessary to transfer the traces from instrument to instrument. Thus a standardized file structure is necessary, and a universal file conversion program must be developed for each instrument. The JCPDS—ICDD is working on this difficulty and has tentatively decided to follow the IUCr in using the CIF/STAR format. CIF/STAR is available now for data archiving, and the PDF-3 will follow rules similar to those used in this format.

As the problems are solved, digitized traces will be accumulated by the ICDD, and when there is a significant number of these data, a set of PDF-3 patterns will be issued. The development of this database will be slow at first, but as the problems are overcome and the applications are extended, this database should become another product of the JCPDS-ICDD.

In addition to PDF-3, there are several other computer products that should appear within the next 2 years. The Metals and Alloys File is being extensively reviewed, and a product is now available. A complete Mineral File will probably appear about every five years.

The CD-ROM is currently the most popular computer media for obtaining the **PDF**. The Crystal Data File is already available on the CD-ROM and the Electron Diffraction Database can also be included on the CD-ROM.

FUTURE OF THE JCPDS-ICDD

The renaissance of powder diffraction in the 1980s will continue into the next decade and probably beyond. New instrumentation will demand new products based on diffraction data. The JCPDS—ICDD is trying to anticipate these changes. The topic is always part of the agenda of the Technical Committee meetings. The Long-Range Planning Committee tries to look ahead 10 to 20 years to recommend new directions for endeavor.

New members for ICDD are continually being sought, and all members are encouraged to participate in as many activities as their time allows. Membership is limited only by interest. The meetings of the Technical Committee are open to anyone wishing to attend, and as new attendees indicate interest and participate in the activities of the JCPDS—ICDD, they are invited into membership. The JCPDS—ICDD financially supports three international meetings, EPDIC in Europe, Denver in the U.S.A., and AXAA in Australia. Most JCPDS—ICDD meetings are held in the Philadelphia area because of the proximity to headquarters, but there are usually open ad-hoc sessions held at Congresses of the International Union of Crystallography and at other technical meetings from time to time. Information on the next scheduled meetings may be obtained at any time from JCPDS—ICDD headquarters.

The JCPDS—ICDD is responding to the change in its market from primarily domestic in the 1960s to primarily international in the 1990s. The market is now about equally divided among North America, Europe and Asia with a small but growing influence from Australia. About 20 percent of the members of the JCPDS—ICDD are from outside North America, and this number is increasing as more users become aware of the activities in which they can participate. The Board of Directors has overseas members, and there are consultants from all the technical areas of the world. Automation has certainly been one of the reasons for the rapid increase in the use of the **PDF** all over the world, but technological developments even in underdeveloped countries are having their effect. All diffractionists are invited to contact the JCPDS—ICDD to see how they can assist in the development of projects. Individuals need not attend the meetings to have a useful role in the future of the **PDF** and related products.

REFERENCES

- Hanawalt, J.D.; Rinn, H.W. *Ind. Eng. Chem. Anal. Ed.* **8** **1936**, 244-250.
- Hanawalt, J.D.; Rinn, H.W.; Frevel, L.K. *Ind. Eng. Chem. Anal. Ed.* **10**, **1938**, 457-512.
- Himes, V.L. and Mighell, A.D. in *Crystallographic Databases*, edited by Allen et al., Eds., International Union of Crystallography, Chester, U.K., 1985; pp144-155.
- Jenkins, R. and Smith, D.K. in *Crystallographic Databases*, edited by Allen, et al., Eds., International Union of Crystallography, Chester, U.K., 1987; pp 158-177.
- Mighell, A.D., Hubbard, C.R., Stalick, J.K. and Holomany, M.A. *NBS*AIDS83: A Manual Describing the Data Format Used in NBS*AIDS83*, JCPDS-International Centre for Diffraction Data, Swarthmore, PA, U.S.A., 1983.
- Smith, G.S.; Snyder, R.L. *J. Appl. Cryst.* **1979**, **12**, 60-65.
- Toby, B.H.; Harlow, R.L.; Holomany, M.A. *Powder Diffraction* **1989**, **4**.
- Villars, P. and Calvert, L.D. (1985) *Pearson's Handbook of Crystallographic Data for Intermetallic Phases*; Vol. 1-3, American Society for Metals, Metals Park, OH, U.S.A.
- deWolff, P.M. (1972) *J. Appl. Cryst.* **5**, 243.